

HAYNES[®] 242[®] alloy

Impact Strength

Product	Condition	Average Impact Strength	
		ft-lb	J
Plate	Solution Annealed	194	263
Plate	Age Hardened*	91	123
Ring	Annealed + Aged*	51	69

*Aged at 1200°F (649°C) / 24 h / air cool.