


HASTELLOY[®] C-22HS[®] alloy

Hardness Profile



HRC = Hardness, Rockwell C Scale

Diameter	% Cold-Worked	Yield Strength (ksi)		Hardness (HRC)	
		1" Below Surface	Mid-Radius	1" Below Surface	Mid-Radius
7.5	50	185.5	180.3	-	-
8	50	175.4	-	-	-
8.25	40	168.1	166.2	38.6	36.1
10	30	162.3	149.8	40.0	35.0

HRC= Hardness Rockwell "C"