

HASTELLOY[®] C-22HS[®] alloy

Compressive Strength

Room Temperature Compressive Strength of 0.75 in Diameter Cold-worked (44%) Bar and Corresponding Tensile Data

Material Condition	Compressive Yield Strength*		Compressive Strength*		Tensile Yield Strength*		Tensile Strength*	
	ksi	MPa	ksi	MPa	ksi	MPa	ksi	MPa
Cold-worked (44%) Bar	163	1124	219	1510	205	1413	210	1448

*Average from two tests