

# HASTELLOY<sup>®</sup> G-35<sup>®</sup> alloy

## Hardness

<b>Form</b>	<b>Hardness, HRBW</b>	<b>Typical ASTM Grain Size</b>
Sheet	87	3.5 - 5
Plate	87	2 - 4.5
Bar	82	1 - 4

All samples tested in solution-annealed condition.

HRBW = Hardness Rockwell "B", Tungsten Indentor.

[Print Page](#)