

HAYNES[®] 556[®] alloy

Impact Properties

Alloy	V-Notch Impact Strength ¹ Room Temperature	
	ft.-lb.	J
-		
800H	239 ²	324 ²
600	180	244
556 [®]	177 ²	240 ²
188	143	194
S	140	190
625	81	110
X	54	73

¹ Average of 4 or more tests

² Samples did not break