

# HASTELLOY<sup>®</sup> G-35<sup>®</sup> alloy

## Impact Strength

Plate Thickness		Test Temperature		Impact Strength*	
in	mm	°F	°C	ft.lbf	J
0.75	19.1	RT	RT	>264	>358

\*Charpy V-Notch Samples

[Print Page](#)