

# HAYNES<sup>®</sup> 242<sup>®</sup> alloy

## Hardness and Grain Size

### Solution Annealed Room Temperature Hardness

<b>Form</b>	<b>Hardness, HRBW</b>	<b>Typical ASTM Grain Size</b>
Sheet	92	5 - 6.5
Plate	94	4 - 6.5
Bar	90	3.5 - 6

HRBW= Hardness Rockwell "B", Tungsten Indentor.