

HASTELLOY[®] C-22HS[®] alloy

Hardness

Material Condition	Hardness, HRC*
Cold-worked (43-47%) Bar	42
Cold-worked (43-47%) Tube	42

*Average values HRC= Hardeness Rockwell "C"