

HAYNES[®] 230[®] alloy

Hardness and Grain Size

Solution Annealed Room Temperature Hardness

Form	Hardness, HRBW	Typical ASTM Grain Size
Sheet	92	4 - 6.5
Plate	92	3 - 5
Bar	90	3 - 5

HRBW = Hardness Rockwell "B", Tungsten Indentor.